


常に最新の印刷環境に適応した
“ブランケット”を開発・製造しています。



Developing and manufacturing printing blankets with features adapted to the latest printing environments.

SUMITOMO S-PRIA BLUE PLUS



オフセット印刷分野 特殊印刷分野等
Offset Printing, Specialized Printing,
and Related Fields

| | | |
|--|-------------------|--------------|
| Surface Colour | | Light Blue |
| Type | | Compressible |
| Thickness | mm | 1.95 |
| Number of ply | | 3 |
| Thickness tolerance | mm | |
| Hardness | ° Shore A | 79 |
| Surface Roughness, Rz | μm | 9.7 |
| Compressibility at 100 N/cm ² | mm | 0.11 |
| | % | 6 |
| Paper Release (max.=100) (*) | without ink | 86 |
| | with ink | 26 |
| Durability test (*) Gauge loss | % | 1.5 |
| | Loss of Compress. | % |
| Cylinder Fitness at | 4 N/mm | mm |
| | 5 N/mm | mm |
| | 6 N/mm | mm |
| Flexibility (*) | degree | 30 |
| Tensile Strength | N/mm | 66 |
| 2 % Modulus | N/mm | 44 |
| Elongation at Break | % | 3.3 |
| Conv. Ink Swell test, Thickness Increase in 24 h | | -0.02 |
| UV Ink Swell test, Thickness Increase in 24 h | | 0.04 |

